IN THE CLAIMS:

1-15. canceled

16. (currently amended) A method of fabricating a non-volatile memory transistor comprising the steps of:

preparing a semiconductor substrate;

forming a gate stack on the substrate, ~~the gate stack comprising~~ as follows:

depositing a high-k dielectric material;

exposing the high-k dielectric material to an ionized species;

in response to the ionized species exposure, inducing trapping centers in the high-k dielectric material;

~~a single charge trapping layer overlying the substrate wherein the charge trapping layer comprises a high-k dielectric material;~~ and

forming an electrode layer overlying the high-k dielectric with the charge trapping centers ~~layer~~; and

forming drain and source regions on opposite sides of the gate stack.

17. (original) A method as in claim 16 wherein the high-k dielectric material comprises at least one of aluminum oxide (Al_2O_3), hafnium oxide (HfO_2), zirconium oxide (ZrO_2), titanium oxide (TiO_2), tantalum oxide (Ta_2O_5), cesium oxide (CeO_2), lanthanum oxide (La_2O_3), tungsten oxide (WO_3), yttrium oxide (Y_2O_3), bismuth silicon oxide ($Bi_4Si_2O_{12}$), barium strontium oxide ($Ba_{1-x}Sr_xO_3$), lanthanum aluminum

oxide ($LaAlO_3$), hafnium silicate ($HfSiO_4$), zirconium silicate ($ZrSiO_4$), aluminum hafnium oxide (AlHfO), aluminum oxynitride (AlON), hafnium silicon oxynitride (HfSiON), zirconium silicon oxynitride (ZrSiON), barium titanate ($BaTiO_3$), strontium titanate ($SrTiO_3$), lead titanate ($PbTiO_3$), barium strontium titanate (BST) ($Ba_{1-x}Sr_xTiO_3$), lead zirconium titanate, lead lanthanum titanate, bismuth titanate, strontium titanate, lead zirconium titanate (PZT ($PbZr_xTi_{1-x}O_3$)) barium zirconium titanate, strontium bismuth tantalate, lead zirconate ($PbZrO_3$), PZN ($PbZn_xNb_{1-x}O_3$), PST ($PbSc_xTa_{1-x}O_3$), or PMN ($PbMg_xNb_{1-x}O3$).

18-19. canceled

20. (currently amended) A method as in claim [[19]] 16 wherein exposing the high-k dielectric material to the ionized species includes exposing the high-k dielectric to a species selected from the group consisting of ~~the plasma exposure comprises at least a plasma~~ oxygen ~~exposure~~, ~~a plasma~~ nitrogen ~~exposure~~, ~~or a plasma~~ and hydrogen ~~exposure~~.

21. (currently amended) A method as in claim [[19]] 16 wherein exposing the high-k dielectric material to the ionized species includes exposing the high-k dielectric material to a [[the]] plasma for an exposure time in the range of about ~~is between~~ 10 seconds and 100 seconds.

22. (currently amended) A method as in claim 16 wherein depositing the high-k dielectric material includes depositing using an ~~the charge trapping layer is deposited by~~ ALD method.

23. (currently amended) A method as in claim 16 further comprising a densification anneal step after the deposition of the high-k dielectric material ~~charge trapping layer~~.

24. (original) A method as in claim 16 wherein the formation of the drain and source regions comprises an angle source and drain implantation.

25. (currently amended) A method as in claim 16 wherein the semiconductor substrate is selected from a group consisting ~~consisted~~ of SOI substrate, bulk silicon substrate, and insulator substrate.

26. (original) A method as in claim 16 wherein the memory transistor is a multi-bit memory transistor.

27. (new) A method as in claim 16 wherein exposing the high-k dielectric material to an ionized species includes using an ion energy in the range of about 10 to 300 keV and a dose in the range of about 1×10^{14} to 1×10^{17}.

28. (new) A method as in claim 16 wherein exposing the high-k dielectric material to an ionized species includes generating a plasma using an inductively coupled plasma (ICP) source.